

Component - Plastics

E121562

SABIC INNOVATIVE PLASTICS US L L C

AMERICAS - RESIN, 1 PLASTICS AVE, PITTSFIELD MA 01201

F600(B)**Polycarbonate (PC), "Lexan", furnished as sheets**

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
(B)	1.5	V-0	3	3	125	110	125
	3.0	V-0	2	3	125	110	125
CL	6.0	V-0	1	3	125	110	125

Comparative Tracking Index (CTI): **2**

Dimensional Stability (%): -

High-Voltage Arc Tracking Rate
(HVT): **4**High Volt, Low Current Arc Resis (D495): **4**

Dielectric Strength (kV/mm): -

Volume Resistivity (10^x ohm-cm): -

NOTE - Material designation may be followed by a color nomenclature consisting of either an alpha/numeric or numeric/alpha combination.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1976-01-07

Last Revised: 2009-06-25

Underwriters Laboratories Inc®

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	V-0 ((B))
			3.0	V-0 ((B))
			6.0	V-0 (CL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m²	-	-
ISO Izod Impact	ISO 180	kJ/m²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m²	-	-

Underwriters Laboratories Inc®